

















# marmoleum ohmex, decibel, acoustic

Marmoleum voldoet aan de eisen van de norm ISO 24011/EN 548.

		Ohmex	Decibel	Acoustic
	ISO 24346 / EN 428	2,5 mm	3,5 mm	4,0 mm
	ISO 10874	Klasse 23	Klasse 23	ISO 10974 Klasse 23
	ISO 10874	Klasse 34	Klasse 33	ISO 10974 Klasse 33
	ISO 10874	Klasse 42	Klasse 41	ISO 10974 Klasse 41
	ISO 24341 / EN 426	2,00 m	2,00 m	2,00 m
	ISO 24341 / EN 426	≤ 32 m	≤ 27 m	≤ 32 m
	ISO 24343-1 / EN 433	< 0,15 mm	< 0,30 mm	< 0,40 mm
	ISO 4918 / EN 425	√	√	√
	ISO 26987 / EN 423	√	√	√
	DIN 51130	R9	R9	R9
	EN ISO 717-2	≤ 5 dB	17 dB	14 dB
	EN 1081	$1 \cdot 10^6 < R1$	$< 1 \cdot 10^8$ Ω - statisch dissipatief	

Marmoleum voldoet aan de eisen van de norm EN 14041



	EN 13501-1	C <sub>fl</sub> -s1	C <sub>fl</sub> -s1	C <sub>fl</sub> -s1
	EN 13893	DS: ≥ 0,30	DS: ≥ 0,30	DS: ≥ 0,30
	EN 1815	< 2 kV	< 2 kV	< 2 kV
	EN 12524	0,17 W/m·K	0,17 W/m·K	0,17 W/m·K